



TEST REPORT

No. : NM140700825

Date : Aug. 05, 2014

Page: 1 of 2

KENT PRECISION CO., LTD

NO.801 HONGQIAO RD, BINHU DISTRICT, WUXI CITY, JIANGSU PROVINCE, CHINA 214072

The following sample(s) was/ were submitted and identified on behalf of the client as:

Sample Name : Shear stud
Sample Number : NM140700825
SGS Ref. No. : SUZML140700693
Product specification : 19×125mm
Material and Mark : SWRCH15A
Test Required : Tensile Test
Date of Receipt : Jul. 30, 2014
Test Period : Jul. 30, 2014 to Aug. 05, 2014

Test result(s) : For further details, please refer to the following page(s)

Signed for SGS-CSTC Standards
Technical Services Co., Ltd.
Nanjing Branch

Time Wang

Time Wang
Authorized signatory



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC Standards Technical Services Co., Ltd.
Nanjing Branch

5-8 Building, Zijin (Baicai) Technology Incubation Special Park, No.1 Guanghua Road, Qinhua District, Nanjing, China 210014 t (86-025) 84502056 f (86-025) 84502737 www.sgsgroup.com.cn
中国·南京·秦淮区光华路1号紫金白下创业特别社区5幢厂房B幢 邮编: 210014 t (86-025) 84502056 f (86-025) 84502737 e sgs.china@sgs.com

Member of the SGS Group (SGS SA)

TEST REPORT

No. : NM140700825

Date : Aug. 05, 2014

Page: 2 of 2

Test Item: Tensile Test

Test Method: ISO 6892-1:2009

| Test item | Specimen type | Tensile strength (R_m) (MPa) | Proof strength ($R_{p0.2}$) (MPa) | Percentage elongation after fracture (A) $L_0=25\text{mm}$ (%) |
|-----------|----------------|--|---|---|
| Result | Round specimen | 461 | 354 | 24.5 |

Sample photo(s):



***** End of report *****



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS Standards Technical Services Co., Ltd.
Nanjing Branch

5-8 Building, Zijin (Baicai) Technology Incubation Special Park, No.1 Guanghua Road, Qinhua District, Nanjing, China 210014 t (86-025) 84502056 f (86-025) 84502737 www.sgsgroup.com.cn
中国·南京·秦淮区光华路1号紫金白下创业特别社区5幢厂房B幢 邮编: 210014 t (86-025) 84502056 f (86-025) 84502737 e sgs.china@sgs.com